



LEMBAGA GETAH MALAYSIA
MALAYSIAN RUBBER BOARD
RUBBER RESEARCH INSTITUTE OF MALAYSIA

Unit Pencirian Bahan
260 Jalan Ampang, 50450 Kuala Lumpur.
Peti Surat 10150, 50908 Kuala Lumpur, Malaysia.
Tel: (6)03-92062000, 9206 3679 Fax: (6)03-42519213
Email: upbac@lgm.gov.my



MS ISO/IEC 17025

TESTING
SAMM NO 069

Our report no. : **LGM/BTK/UPB/5.10/CP/0707/2451-2477**
Your reference no. :

Siam Sempermed Corporation Limited
(Attn : Tasnee Hasalem)
110 Kanjanavanit Road Pahtong, Hatyai
Songkhla 90230
Thailand.

Fax : 66 7429 1650


Analytical Result

We have received your sample under the covering of your letter dated 20/07/2007. The sample has been analyzed as per your request and the results are reported below:

Five g sample was acetone extracted overnight. The extract was rotary evaporated to near dryness and then made up to 5 mL in dichloromethane. 5 microliters aliquote was spotted on TLC plate. The identity and concentration of the chemicals were determined by comparing them to authentic reference material. Nd means not detected at detection limit of 0.01%.

Sample description : **Sempermed Latex Exam PowderFREE Glove**
65 MMLCT0101230SD 190707M25T06C (006195448)
Date Received : **25/07/2007**
Date tested : **16/08/2007**
Method : **UPB/P/002**

No	Chemical Test	Results
1.	Tetramethylthiuram disulphide (TMTD) (%)	Nd
2.	Mercaptobenzothiazole (MBT) (%)	Nd
3.	Zinc Mercaptobenzothiazole (ZMBT) (%)	Nd
4.	Zinc diethyldithiocarbamate (ZDEC) (%)	0.06
5.	Zinc dimethyldithiocarbamate (ZDMC) (%)	Nd
6.	Zinc pentamethylene dithiocarbamate (ZPMC) (%)	Nd
7.	Zinc dibutyldithiocarbamate (ZDBC) (%)	0.12
8.	Zinc dibenzylidithiocarbamate (ZBED) (%)	Nd
9.	Butylhydroxytoluene (BHT) (%)	Nd
10.	Butylhydroxyanisole (BHA) (%)	Nd
11.	Wingstay L (%)	0.64


Dr Faridah Hanim Ab Hanan
Head of Unit
Materials Characterization Unit
MALAYSIAN RUBBER BOARD

24 August 2007